

## DELTA EG™ MODULE

**Delta EG™ Modules** have the highest insulating value achievable in a ceramic fiber lining. Each module is comprised of layered blanket under compression to insure a tight seal and a “spring-back” action not found in typical wallpaper linings.

Noted features of a **EG™ Module** lining are:


- Fast & Easy installation
- No layout required.
- Low heat storage and fuel costs
- Thermal shock resistance speeds up heat ups and cool downs for quick turn-around times.
- Manufactured in the USA with Unifrax Blanket

Typical Applications for **EG™ Modules** are:


- Stress Relieving Furnaces
- Annealing Furnaces
- Car Bottom & Heat Treating Furnaces
- Process Heaters
- Reheat Furnaces
- Kiln & Boiler Linings
- Incineration Equipment
- Stack Linings
- Soaking Pit Covers
- Ladle Covers & Ladle Preheaters
- Forge Furnaces

Size & Densities Available

- 8, 9.3, 10.7, 12 (Lbs/Ft<sup>3</sup>)
- Standard Sizes range from 24" x 24" to 12" x 12" in thicknesses from 2" to over 12"
- Custom sized & pre-cut modules are also available for a seamless installation.



### Typical EG™ Installation Method



1. Weld U-Hanger to furnace shell (*Start & Finish Modules Only*)
2. Insert EG™ Module onto U-Hanger (*Middle Modules Only*)
3. Insert H-Hanger into EG™ Module
4. Weld H-Hanger to Shell
5. Repeat process as shown until desired area is covered.

#### **Corporate Office**

Ph: 281.391.1320 / Toll Free 800.430.2226

Fax: 281.391.2015

Web: <http://www.deltarefractories.com>

Email: [DRISales@deltarefractories.com](mailto:DRISales@deltarefractories.com)

#### **Mailing Address**

21557 Provincial Blvd  
Katy, Texas 77450

**Typical Product Parameters**

Chemical Composition	Grade (Recommended Operating Temperature)		
	1800°F (1800°F)	2300°F (2150°F)	2600°F (2450°F)
Al <sub>2</sub> O <sub>3</sub>	31-35%	43-47%	29-31%
SiO <sub>2</sub>	50-54%	53-57%	53-55%
ZrO <sub>2</sub>	5%	—	15-17%
Fe <sub>2</sub> O <sub>3</sub>	1.3%	Trace	—
TiO <sub>2</sub>	1.7%	Trace	—
MgO	*0.5%	—	—
CaO	≤ 7.5%	—	—
Na <sub>2</sub> O <sub>3</sub>	—	< 0.5%	—
Alkali	—	0.05%	—
Leachable Chlorides	—	< 10 ppm	< 10 ppm
Other Inorganics	—	0.85%	—
*MgO and other trace elements			



**Corporate Office**

Ph: 281.391.1320 / Toll Free 800.430.2226

Fax: 281.391.2015

Web: <http://www.deltarefractories.com>

Email: [DRISales@deltarefractories.com](mailto:DRISales@deltarefractories.com)

**Mailing Address**

21557 Provincial Blvd  
Katy, Texas 77450